

# Skin Care

## Blurring / Prep step

### Face Primer

	Ingredients	INCI	%	Supplier
A	Water	Water	QS	-
	Carbopol Ultrez 10	Carbomer	0.10	Lubrizol
	Propylene Glycol	Propylene Glycol	5.00	-
	Pemulen TR-1	Acrylates/C10-30 Alkyl Acrylate Crosspolymer	0.10	Lubrizol
	6290 Berry Wax	Rhus Verniciflua Peel Cera	10.00	KahlWax
B	Jjoba Oil Colourless CP RBD	Simmondsia Chinesis Seed Oil	5.00	IMCD/Jan Dekker
	Floviva Apricot Kernel Oil Ref	Apricot Kernel Oil	5.00	Protec Botanica
	Tocomix L50 IP	Tocopherol	0.20	IMCD/Jan Dekker
	Montanov S	Coco-Glucoside & Coconut Alcohol	3.00	Seppic
	Xiameter PMX-200 50cs	Dimethicone	1.25	Dow
	COD Dispersion		6.00	SunChemical
	C88-0103	Talc & Titanium Dioxide	2.50	SunChemical
C	NaOH (12.5%)	Aqua, Sodium Hydroxide	0.50	-
	Euxyl PE 9010	Phenoxyethanol (and) Ethylhexylglycerin	1.00	Schülke & Mayr

1. Blend water & Carbomer without heating or agitation. Wait for 10 minutes.
2. When the carbomer has sedimented, add first Propylene Glycol then, under stirring, Pemulen TR-1.
3. Heat phase A (under stirring) and phase B separately to 80°C.
4. Add Part B to A under agitation, to form the emulsion
5. Add the NaOH under stirring at 60°C ; mix for 1 to 3 minutes.
6. Cool down to below 40°C, then add preservative to the batch and mix well ; fill into appropriate container.

"Although the data supplied above are believed to be correct, the data are presented without any representation or warranty concerning the suitability, performance or correctness of the product for a particular application or use. Significant variations can occur between test results and results obtained in actual use. We strongly advise that before purchase the buyer test the product in the specific intended application under conditions expected during use. Suggestions made by Sun Chemical Corporation are our opinion only and there is no warranty of the results to be obtained."